

MILBRO REFRACTORIES, INC.

MILCOTE 3000 P

MILCOTE 3000 P is a dry, phosphate bonded, super duty mortar MILCOTE 3000 P exhibits good strength and resistance to cracking when applied. Excellent resistance to metal and slag attack. It can be mixed with water to the desired consistency for troweling, dipping or brushing.

Service Temperature
Mixing Water Required

3000° F
As Desired

TYPICAL CHEMICAL ANALYSIS

Al ₂ O ₃	46.7
SiO ₂	48.0
Fe ₂ O ₃	1.0
TiO ₂	0.6
MgO	0.3
CaO	1.7
Alkalies	0.2