

MILBRO REFRACTORIES, INC.

MILCOTE 70 C

MILCOTE 70 C is a high alumina, wet, heat setting mortar, with carbon addition. Used for laying high alumina and fireclay brick when non-stick characteristics are required. Excellent strength throughout the temperature range.

Service Temperature	3150°F
Material Required for Estimating	420 lbs./M 9 in. equiv.
Mixing Water Required	Use as received

TYPICAL CHEMICAL ANALYSIS (DRY)

Al ₂ O ₃	69.5
SiO ₂	18.5
C	10.0
LOI	3.4