

# MILBRO REFRACTORIES, INC.

## MILCOTE 75C

MILCOTE 75 C is a high alumina, wet, heat setting mortar, with carbon addition. Used for laying high alumina and fireclay brick when non-stick characteristics are required. Excellent strength throughout the temperature range.

<b>Service Temperature</b>	<b>3150°F</b>
<b>Material Required for Estimating</b>	<b>420 lbs./M 9 in. equiv.</b>
<b>Mixing Water Required</b>	<b>Use as received</b>

### TYPICAL CHEMICAL ANALYSIS (DRY)

Al <sub>2</sub> O <sub>3</sub>	69.5
SiO <sub>2</sub>	18.5
C	10.0
LOI	3.4