

# MILBRO REFRACTORIES, INC.

## MILPLAS SUPER AS

A super duty, air setting, plastic refractory. Excellent resistance to thermal spalling and mechanical shock, while volume stability and excellent load bearing properties gives MILPLAS SUPER AS, distinct advantages in a variety of high temperature applications. These applications include upper sidewalls in aluminum melting and/or holding furnaces, boiler & forge furnace linings, as well as linings for incinerators, dryers, heaters and combustion chambers.

<b>Service Temperature</b>	<b>3000° F</b>
<b>Melting Point</b>	<b>3125° F</b>
<b>Material Required for Estimating</b>	<b>145 lbs./ft<sup>3</sup></b>

### TYPICAL CHEMICAL ANALYSIS

Al <sub>2</sub> O <sub>3</sub>	45.6
SiO <sub>2</sub>	48.8
Fe <sub>2</sub> O <sub>3</sub>	1.4
TiO <sub>2</sub>	1.8
MgO	0.1
CaO	0.1

### TYPICAL PHYSICAL PROPERTIES

Temperature °F	Modulus of Rupture, psi	Cold Crushing Strength, psi	Linear change %
220°F	250	850	0.3 S
1500°F	225	900	0.4 S
2000°F	450	1600	0.6 S
2500°F	525	2100	0.5 E
2910°F	1100	4000	1.3 E

All data shown is based on average of standard ASTM procedures, unless otherwise indicated. Results are subject to reasonable deviation and should not be used for specification purposes.

All data shown is based on average of standard ASTM procedures, unless otherwise indicated. Results are subject to reasonable deviation and should not be used for specification purposes.